

Cogne grades for Aerospace



	CAS grade	AISI	Wr. Nr.	EN	UNS	AMS
Precipitation hardening	AC155	15-5PH	1,4545	X5CrNiCu15-5	S15500	AMS 5659 Type 1 AMS 5659 Type 2
	AC174	17-4PH	1,4542	X5CrNiCuNb16-4	S17400	AMS 5643 AMS 5622 Type 1 AMS 5622 Type 2
	AC286	660 A286	1.4980 1.4944	X6NiCrTiMoVB25-15-2 X6NiCrTiMoV26-15	S66286	AMS 5731, AMS 5732 AMS 5734, AMS 5737
Austenitics	AC303	303	1.4345	X8CrNiS18-9	S30300	AMS 5640
	AC304L	304	1.4307 1.4301	X2CrNi18-9 X5CrNi18-10	S30403 S30400	AMS 5647 AMS 5639
	AC310	310	1.4845	X8CrNi25-21	S31008	AMS 5651
	AC316	316	1.4401 1.4404	X5CrNiMo17-12-2 X2CrNiMo17-12-2	S31600 S31603	AMS 5648 AMS 5653
	AC321	321	1.4541	X6CrNiTi18-10	S32100	AMS 5645
	AC347	347	1.4550	X6CrNiNb18-10	S34700	AMS 5646
Martensitics	AC410	410	1.4006	X12Cr13	S41000 S41040	AMS 5613
	AC152	XM-32	1,4939	X12CrNiMoN12	S64152	AMS 5719 Type 1 AMS 5719 Type 2
	AC415	415M	1.4418	X4CrNiMo16-5-1		
	AC416	416	1.4005	X12CrS13	S41600	AMS 5610
	AC431	431	1.4057	X17CrNi16-2	S43100	
	AC440C	440C	1,4125	X105CrMo17	S44004	AMS 5630